

AMENDMENTS TO THE SPECIFICATION

Amend the paragraph at page 9, lines 11-17, as follows:

The first crystallized glass of the present invention preferably consists, as represented by mol% based on the following oxides, essentially of from 30 to 65% of  $\text{SiO}_2$ , from 5 to 35% of  $\text{Al}_2\text{O}_3$ , from 1 to 15% of  $\text{TiO}_2+\text{ZrO}_2$ , from 0 to 30% of  $\text{Na}_2\text{O}$ , from 5 to 30% of  $\text{K}_2\text{O}$ , from 0 to 15% of  $\text{Li}_2\text{O}$ , from 0 to 15% of  $\text{MgO}$ , from 0 to 15% of  $\text{CaO}$ , from 0 to 15% of  $\text{SrO}$ , from 0 to 15% of  $\text{BaO}$ , from 0 to 15% of  $\text{ZnO}$ , from 0 to 15% of  $\text{B}_2\text{O}_3$ , from 0 to 15% of  $\text{P}_2\text{O}_5$  and from 0 to 15% of  $\text{Y}_2\text{O}_3$ .